

# LUISO W25

for nitriding & nitrocarburizing

**DAM Härtetechnik**

[www.stopoffpaints.com](http://www.stopoffpaints.com)



- without solvents
- environment friendly and fragrance-free
- viscosity and course may be adjusted by water
- drying time appr. 30 minutes only
- very good protection properties

## Application

**LUISO W25** is a fragrance-free and solvent-free stop off paint for nitriding and nitrocarburizing. The stop off paint is delivered ready for painting.

Before using, **LUISO W25** should be stirred up shortly and then applied with a paint brush. The work pieces to be treated must be free of grease and dirt! One layer is sufficient. To avoid evaporation the cans should be sealed after use. To restore normal viscosity the stop off paint can be diluted by adding up to 2 % water. No special thinners are necessary.

The dry off time for **LUISO W25** is 30 minutes. Unwanted paste residues may be removed easily with water.

After heat treatment **LUISO W25** residues may be removed by using water.

## Packing

**LUISO W25** to be delivered in PP-cans of 1, 5 or 10 kg.

## Storage

**LUISO W25** is sensitive to frost. Storage at room temperature is recommended. Opened cans should be sealed hermetically after use. Storage time should not exceed 12 months.



**Contact**

For further information please call us under telephone +49 (0)621 / 454 9 666

# LUISO W25

for nitriding & nitrocarburizing

# DAM Härtetechnik

[www.stopoffpaints.com](http://www.stopoffpaints.com)

## Data

Consistency	painting (dipping, spraying)
Thinning	up to 2 % water
Working temperature	room temperature
Drying time	30 minutes only
Surface	at least 0,3 - 0,5 mm
Packing	PP-cans
Packing unit	1 kg / 5 kg / 10 kg
Precaution	none
Storage	up to one year

## Awards

In 2004 the Economic Development Rheinland-Pfalz (ISB) GmbH awarded stop off paints LUISO a prize for the successful development and market introduction.



Economic Development  
Rheinland-Pfalz

# DAM Härtetechnik

[www.stopoffpaints.com](http://www.stopoffpaints.com)

Am Bubenpfad 2, 67065 Ludwigshafen, Deutschland  
Tel: +49 (0)621 - 4549666 / Fax: +49 (0)621 - 4549667

© Copyright 2008 DAM Härtetechnik GmbH

All information in this literature we believe to be reliable. No warranties, express or implied are made, any implied warranty of fitness for a particular purpose is expressly disclaimed. We recommend that the prospective user determine the suitability of our materials and recommendations before adopting them on a commercial scale. Patents or other legal rights may not be violated under any given circumstances.

04/2008